

Product Data Sheet

# NC-771 Pb-Free, No-Clean Flux

## Benefits

- Backwards compatible with eutectic Sn/Pb
- Ideal for high-reliability electronic circuitry
- Benign, non-sticky, post reflow residue
- Provides excellent wetting
- Wide reflow process window

## Introduction

**NC-771** is a halide-free, low residue, all-purpose liquid flux that can be used in a standard Sn/Pb or Pb-Free rework or soldering process. It is a rosin-free material that exhibits excellent wetting to OSP, ENIG, HASL, Immersion Ag and other common PWB board finishes. In addition to the aesthetic benefits, the ultra-low post reflow residue is non-tacky and will not interfere with probe testing.

## Process Recommendations

**NC-771** is a multi-purpose flux that can be used in an SMT rework process or almost any soldering application that requires the addition of a liquid flux. Typical application methods include a flux pen that allows you to apply a precise amount of flux to the solder joint. It can also be sprayed on for use in a selective soldering process or dispensed out a flux bottle. Care should be taken not to flood the solder joint and to apply the flux only to areas that will be exposed to complete heating from the solder iron or rework tool.

## Packaging

**NC-771** can be supplied in flux pens or in plastic containers.

## Shelf Life:

1 year when stored at 0 - 30°C

## Material Safety Data Sheet

The MSDS for this product can be found online at <http://www.indium.com/techlibrary/msds.php>

## Technical Support

Indium Corporation's internationally experienced engineers provide in-depth technical assistance to our customers. Thoroughly knowledgeable in all facets of Material Science as it applies to the electronics and semiconductor sectors, Technical Support Engineers provide expert advice in solder properties, alloy compatibility and selection of solder preforms, wire, ribbon and paste. Indium Corporation Technical Support engineers provide Rapid Response to all technical inquiries.



## Physical Properties

Test	Result
Color:	Clear
Flash Point (°F TCC)	12
Smell	Alcoholic

## J-STD-004A TESTING RESULTS

Test	Result
• Flux Type Classification	ORLO
• SIR	Pass
• Copper Mirror	Type L
• Silver Chromate	Pass
• Fluoride Spot Test	Pass
• Corrosion	Pass
• Acid Value (nominal)	32.5 mg KOH/gm
• Specific Gravity (nominal)	0.825
• Flux Solids (typical)	5.0%

All information is for reference only. Not to be used as incoming product specifications.

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices.

Form No. 97675 R3

S O L D E R

INDIUM CORPORATION OF AMERICA®

www.indium.com  
 askus@indium.com  
 PRC +86 (0)512 628 34900  
 SINGAPORE +65 6 268 8678  
 UK +44 (0) 1908 580400  
 USA +1 315 853 4900



ISO 9001  
REGISTERED