

PRODUCT INFORMATION SHEET

PRODUCT NUMBER:	PC 5131 BASE / PC 5131 ACTIVATOR
DESCRIPTION:	POLYURETHANE RESIN SYSTEM

PHYSICAL PROPERTIES

Base Component

Appearance:	White Liquid
Viscosity:	16 - 20 poise
Specific Gravity:	1.16 - 1.18 g/cm ³

Activator Component

Appearance:	Brown Liquid
Viscosity:	2 - 3 poise
Specific Gravity:	1.21- 1.23 g/cm ³

Mixture

Mix ratio Base : Activator:	3.33: 1 parts by weight
Gelation Time 100g @ 25°C (min):	30 - 60

Storage

All materials should be stored in sealed containers in well ventilated areas, ideally maintained at 20-25°C and care must be taken to avoid leakage, spillage and contamination. The minimum shelf life of the unopened container is 6 months.

Safety in Handling – see relevant material safety data sheet. The above data refers to typical laboratory test results or estimated laboratory values. Full manufacturing specifications are available on request. The application, use and processing of our products is the responsibility of the user. The technical or other advice, information or data provided by us whether verbally, in writing or by way of trials is given without guarantee or warranty.