

P/S 870 Class C corrosion inhibitive sealant

Description

P/S 870 Class C is a corrosion inhibitive sealant. It has a service temperature range from -54°C (-65°F) to 121°C (250°F), with intermittent excursions up to 135°C (275°F). This material acts as an effective barrier against the common causes of corrosion on aluminium alloys or between dissimilar metals. The cured sealant maintains elastomeric properties after limited exposure to both jet fuel and aviation gas.

P/S 870 Class C is a two-part, manganese dioxide cured polysulfide compound. The uncured material is designed for roller and faying surface sealing applications. It cures at room temperature to form a resilient sealant having excellent adhesion to common aircraft substrates.

This product is qualified to several manufacturers' specifications. Please contact PRC-DeSoto Europe for further information.

The following tests are in accordance with MIL-S-81733 Type IV and other OEM specifications test methods.

Application properties (typical)

Colour			
Part A			Black
Part B			White
Mixed			Grey
Mixing ratio			Part A:Part B
By weight			17:100
Base viscosity			
(Brookfield #5 @ 10 rpm),			
Pa-s (Poise)			250 (2,500)
Application life and cure time @ 25°C (77°F), 50% RH			
	Application life (hours)	Assembly time (hours)	Cure time to 30 A Durometer (days)
C-12	12	20	14
C-24	24	80	21
C-48	48	168	56

Performance properties (typical)

Cured in accordance with MIL-S-81733 Type IV	
Cured specific gravity	1.50
Nonvolatile content, %	90
Ultimate cure hardness,	
Durometer A	50
Soluble chromate, %	4
Peel strength, N/25 mm (pli), 100% cohesion	
JP-4 fuel immersion, 2 days @ 60°C (140°F)	
MIL-A-8625 (Anodized aluminium)	93 (21)
MIL-T-9046 (Titanium comp. C)*	116 (26)
3% NaCl-H ₂ O immersion, 7 days @ 60°C (140°F)	
MIL-A-8625 (Anodized aluminium)	111 (25)
MIL-T-9046 (Titanium comp. C)*	116 (26)
*Primed with PR-148 Adhesion Promoter	
Tensile strength, KPa (psi)	
Standard cure, 14 days @ 25°C (77°F), 50% RH	1724 (250)
Elongation, %	
Standard cure, 14 days @ 25°C (77°F), 50% RH	250
Low temperature flexibility @ -54°C (-65°F) - No cracking, checking or loss of adhesion.	
Resistance to hydrocarbons - 7 days @ 60°C (140°F) immersed in Type III JRF.	
Weight loss, %	7.0
Flexibility - No cracks after bending 180 degrees over 3.18 mm (0.125 inch) mandrel.	
Repairability to itself - Excellent to both fresh cured as well as fuel aged and abraded fillets.	
Lap shear strength, KPa (psi), 100% cohesion	
BMS 10-11 (Epoxy primer)	
Standard cure, 14 days @ 25°C (77°F), 50% RH	1601 (232)
Type III fuel, 7 days @ 49°C (120°F)	1656 (240)
3% NaCl-H ₂ O, 7 days @ 49°C (120°F)	1725 (250)
Salt spray (fog) test for 1000 hrs. (ASTM B117) - No corrosion to base substrate or deterioration of sealant.	

P/S 870 Class C corrosion inhibitive sealant

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Surface preparation

Immediately before applying sealant to primed substrates, the surfaces should be cleaned with solvents. Contaminants such as dirt, grease, and/or processing lubricants must be removed prior to sealant application.

A progressive cleaning procedure should be employed using the appropriate solvents and new lint free cloth (reclaimed solvents or tissue paper should not be used). Always pour solvent on the cloth to avoid contaminating the solvent supply. Wash one small area at a time.

It is important that the surface is dried with a second clean cloth prior to the solvent evaporating to prevent the redeposition of contaminants on the substrate.

Substrate composition can vary greatly. This can affect sealant adhesion. It is recommended that adhesion characteristics to a specific substrate be determined prior to application on production parts or assemblies.

Mixing instructions

P/S 870 Class C is supplied in a two-part kit. Mix according to the ratios indicated in the application properties section. Mix Part A and Part B separately to uniformity, then thoroughly mix entire contents of both parts of kit together taking care to avoid leaving unmixed areas around the sides or bottom of the mixing container.

Storage life

The storage life of P/S 870 Class C is at least 6 months when stored at temperatures below 27°C (80°F) in original unopened containers.

Health precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An MSDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For sales, ordering and technical information, please contact PRC-DeSoto Europe, Ltd.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.